

MIDALLOY ER2209 BARE WIRE

CLASSIFICATION

- AWS 5.9 Class ER2209 / ASME SFA 5.9 Class ER2209
- UNS# S39209 A#8 F#6

DESCRIPTION

- MIDALLOY ER2209 bare welding wire is used to weld standard duplex stainless steels such as UNS S31803.
- This product over matches the base metal by 2-3% in nickel content so as to give the correct balance of austenite and ferrite in the microstructure in the as-welded condition.

APPLICATIONS

- Used for pipe work and general fabrication in the offshore oil, gas and chemical process industries.
- Alloy offers high strength with good ductility and excellent corrosion resistance.

TYPICAL CHEMISTRY

C	Cr	Ni	Mo	Mn	Si	P	S	N
.013	22.7	8.7	3.2	1.75	.41	.015	.002	.17

- Duplex weld metal microstructure with austenite + 30-50% ferrite.

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	118,900 PSI
YIELD STRENGTH	84,100 PSI
ELONGATION IN 2"	28%

RECOMMENDED WELDING PARAMETERS

PROCESS	DIAMETER	VOLTAGE	AMPERAGE	GAS/FLUX*
TIG (GTAW)	1/16"	14-18	90-130	100% Ar
	3/32"	15-20	120-175	100% Ar
	1/8"	15-20	150-220	100% Ar
MIG (GMAW)	.035" SHORT ARC	19-21	90-120	90 He/7.5 Ar/2.5 CO ₂ ,
	.045" SPRAY ARC	28-32	180-250	98 Ar/2 O ₂
	1/16" SPRAY ARC	29-33	200-300	98 Ar/2 O ₂
SAW	3/32"	28-30	275-325	SOUDOKAY IND 24
	1/8"	28-30	350-400	SOUDOKAY IND 24

* Other gas may be used – call with specific applications

Heat input restrictions 12,000 + 63,000 joules/IN

PACKAGING

- TIG 10 lb. tube/60 lb. carton
- MIG 30 lb. spool
- SUB-ARC 60 lb. coil

1/27/09

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.

Office and Corporate Warehouse
630 Axminister Drive
Fenton, MO 63026 • 636-349-6000 • 800-776-3300
Fax 636-349-2240

