

MIDALLOY CHROMAX E310HC-16 COATED ELECTRODE

CLASSIFICATION

- AWS 5.4 Class E310HC-16 / ASME SFA 5.4 Class E310H-16

DESCRIPTION

- MIDALLOY CHROMAX E310HC-16 is AC-DC Titania Coated Electrode

APPLICATION

- For welding or repairing high alloy head and corrosion resistant castings of the same general composition, which are designated HK by the alloy castings institute.

TYPICAL CHEMISTRY

C	Cr	Ni	Mo	Mn	Si	P	S	Cu
.35-.45	27.0	20.4	.10	1.30	.45	.015	.005	.08

TYPICAL MECHANICAL PROPERTIES

TENSILE STRENGTH	89,900 PSI min.
ELONGATION IN 2"	10% min.
HEAT TREATMENT	NONE

WELDING PARAMETERS

DIAMETER	VOLTAGE	AMPERAGE	
		FLAT	VERTICAL & OVERHEAD
3/32"	24-28	70-85	65-75
1/8"	26-30	85-110	80-90
5/32"	28-32	110-140	100-120
3/16"	28-32	120-160	110-130

STANDARD PACKAGING

- 3/32" 8 lb. can / 48 lb. box
- 1/8" 10 lb. can / 60 lb. box
- 3/16" 10 lb. can / 60 lb. box
- 5/32" 10 lb. can / 60 lb. box

The contents of this publication are presented for informational purposes only, and while every effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described herein or their use or applicability. We reserve the right to modify or improve the designs or specifications of such products at any time without notice.